

NOTES:

This information is to be used only as a guide.  
 Products on this list can change without notice.

ODOT QPL website: <http://www.oregon.gov/ODOT/HWY/CONSTRUCTION/QPL/QPIndex.shtml>

## ODOT 2002 SPECIFICATIONS

### TABLE 2320-1

Property	Drainage (1)		Riprap (1)		Subgrade	Embankment	Pavement (1)
	Type 1	Type 2	Type 1	Type 2			
Grab Tensile Strength	80	180	200	260	180	230	76
Grab Elongation	15%		15%				50%
Burst Strength	130	290	320	435	290	435	
Puncture Strength	35	35	80	80	80	110	
AOS	0.212		0.212		0.6	0.6	
	70 Sieve		70 Sieve		30 Sieve	30 Sieve	
Permittivity	0.5 s-1		0.5 s-1		0.01 s-1	.01 s-1	
UV Stability			70%				
Wide Strip Tensile							
Asphalt Retention (3)							0.2 g/sy
Melting Point							299° F
Mirafi	140NL	170N	180N	1120N	500X	1100N	Mirapave 400

12.5' x 360'	15' x 300'	15' x 300'	15' x 300'	12.5'x432'	15' x 300'	12.5'x360'
15'x360'				15'x360'		
				17.5'x309'		