



Mirafi[®] 1160N

Mirafi[®] 1160N is a needlepunched nonwoven geotextile composed of polypropylene fibers, which are formed into a stable network such that the fibers retain their relative position. Mirafi[®] 1160N is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs (N)	380 (1691.0)	380 (1691.0)
Grab Tensile Elongation	ASTM D4632	%	50	50
Trapezoid Tear Strength	ASTM D4533	lbs (N)	140 (623.0)	140 623.0)
CBR Puncture Strength	ASTM D6241	lbs (N)	1025 (4561.3)	
Apparent Opening Size (AOS) ¹	ASTM D4751	U.S. Sieve (mm)	100 (0.15)	
Permittivity	ASTM D4491	sec ⁻¹	0.7	
Flow Rate	ASTM D4491	gal/min/ft ² (l/min/m ²)	50 (2037.0)	
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	70	

¹ ASTM D4751: AOS is a Maximum Opening Diameter Value

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D5261	oz/yd ² (g/m ²)	13 (440.7)
Thickness	ASTM D5199	mils (mm)	118 (3.2)
Roll Dimensions (width x length)	--	ft (m)	15 x 150 (4.5 x 46)
Roll Area	--	yd ² (m ²)	250 (209)
Estimated Roll Weight	--	lb (kg)	205 (93)

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2011 TenCate Geosynthetics North America
Mirafi[®] is a registered trademark of Nicolon Corporation

